

PRODUCT DATASHEET



PAROC Pro Loose Wool BL

Loose wool with low binder content

Multiformed insulations for columns and tanks as well as ovens in the food processing industry etc.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Package Type

Plastic sack, 15 kg/package

Properties

| PROPERTY | VALUE | ACCORDING TO |
|--|-------------------------|--------------|
| FIRE PROPERTIES | | |
| Reaction to Fire, Euroclass | A1 | EN 13501-1 |
| MOISTURE PROPERTIES | | |
| Water Absorption, Short Term WS, (W _p) | ≤ 1 kg/m ² 1 | EN 1609 |

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries international use (general information).