

PAROC Section AluCoat T



Short Description

Stone wool pipe section with reinforced aluminium foil facing. Tape fastening on the longitudinal seam.

Application

Thermal and condensation insulation of pipework and air ducts.

Application / Marine

Stone wool pipe section with reinforced aluminium foil facing. Tape fastening on the longitudinal seam.

Technical Properties

Maximum Operating Temperature

250 °C

Surface temperature of the facing must not exceed +80°C (temperature restriction determined in accordance with heat resistance of adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Thickness

20-100 mm

Pipe Section Length

1200 mm

Inner Diameter

12-273 mm

Thermal Properties

Thermal Conductivity in 10 °C, λ_{10} 0.034 W/mK

Thermal Conductivity in 50 °C, λ_{50} 0.037 W/mK

Thermal Conductivity in 100 °C, λ_{100} 0.042 W/mK

Thermal Conductivity in 150 °C, λ_{150} 0.049 W/mK


Thermal Conductivity in 200 °C, λ_{200} 0.059 W/mK

Values announced by manufacturer.

Environment

PAROC Section AluCoat T can be used to satisfy the requirements as given in the tables for Environmental Thickness in BS5422.

Paroc can offer help and assistance to customers to confirm that the insulation systems proposed do in fact, achieve the necessary performance criteria. PAROC Section AluCoat T conforms to BS3958-4.



0809

Packaging

Carton on Pallet, Plastic on Pallet

Single Package Size

Carton 300x400x1200mm

Pallet Size

1200x1200mm

Fire Properties

Reaction to Fire, Euroclass

A2_L - s1, d0

Fire Classification

Non-combustible

Fire Classification (Surface)

Class 0

Marine Fire Classification

Non-combustible

Surface Flammability (Marine)

Surface flammability

In accordance with

EN 13501-1

In accordance with

BS 476 Part 4

In accordance with

BS 476 Part 6 and 7

In accordance with

IMO FTP Code Part 1

In accordance with

IMO FTP Code Part 2 and 5



PAROC OY AB, P.O. Box 47 (Läkkisepäntie 23), FI-00621 Helsinki Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, www.paroc.com

The information in this data sheet represents the sole and comprehensive description of the condition of the product and its technical properties. However, the content of this data sheet does not mean granting a commercial guarantee. In so far as the product is used in an area of use which is not provided for in this data sheet, we cannot warrant its suitability for said area of use unless the suitability was expressly confirmed by us upon request. This data sheet replaces all previous ones. As a result of constant further development of our products we reserve the right to make alterations to data sheets. PAROC and red and white stripes are registered trade marks of Paroc Oy Ab. © Paroc Group 2009.