

PAROC Lamella Mat 50 AluCoat



Short Description

Stone wool lamella mat with a reinforced aluminium foil facing

Application

Thermal and condensation insulation of air ducts and other ventilation ducts and equipment.

Application / Marine

Thermal insulation for ducts.

Technical Properties

Nominal Density

50 kg/m³

Maximum Operating Temperature

250 °C

The surface temperature of the facing must not exceed +80°C (temperature restriction determined in accordance with the heat resistance of adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Thickness

20 - 100 mm

Tolerances according to SFS 5454.

Packaging

Package Type

Plastic

Package on Request

Pallet

Fire Properties

Reaction to Fire, Euroclass

A2 - s1, d0

Fire Classification

Non-combustible

Fire Classification (Surface)

Class 0

Marine Fire Classification

Non-Combustible

Surface Flammability (Marine)

Low flame-spread

In accordance with

EN 13501-1

In accordance with

BS 476 Part 4

In accordance with

BS 476 Part 6 and 7

In accordance with

IMO FTP Code Part 1

In accordance with

IMO FTP Code Part 2 and 5

Thermal Properties

Thermal Conductivity in 10 °C, λ_{10} 0.039 W/mK

Thermal Conductivity in 100 °C, λ_{100} 0.053 W/mK

Thermal Conductivity in 200 °C, λ_{200} 0.085 W/mK

Values announced by the manufacturer.

Mechanical Properties


Compressive Stress at 10 % deformation (Declared), CS(10), In accordance with (σ_{10})

≥6 kPa

EN 826

Environment

PAROC Lamella Mat 50 AluCoat can be used to satisfy the requirements as given in the tables for Environmental Thickness in BS5422. Paroc can offer help and assistance to customers to confirm that the insulation systems proposed do in fact, achieve the necessary performance criteria. PAROC Lamella Mat 50 AluCoat conforms to BS3958-4.



0809



PAROC OY AB, Technical Insulation, PO BOX 294, FI-01301 Vantaa, Tel. +358 46 876 8000, Fax +358 46 876 8003, www.paroc.com

Warranty: Our recommendations are based on our most up-to-date knowledge and experience. As the products are used outside our control we cannot take responsibility for any damage which may be caused when using the prod This product data sheet replaces all earlier ones. Because of constant development all information is subject to change without notice.