

# PAROC Lamella Mat AluCoat

(PAROC Lamella Mat 35 AluCoat)



## Short Description

Stone wool lamella mat with reinforced aluminium foil facing.

## Application

Thermal and condensation insulation of air ducts and other ventilation ducts and equipment.

## Technical Properties

### Nominal Density

35 kg/m<sup>3</sup>

### Maximum Operating Temperature

250 °C

The surface temperature of the facing must not exceed +80°C (temperature restriction determined in accordance with the heat resistance of adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

## Dimensions

### Width x Length

Width 1000 and 500 mm, varies by factory. Length 2500 - 10000 mm depending on thickness. mm

### Thickness

20 - 100 mm mm

## Packaging

Plastic

### Package on Request

Pallet

## Fire Properties

### Reaction to Fire, Euroclass

A2 - s1, d0

### Marine Fire Classification

Non-combustible

### Surface Flammability (Marine)

Low flame-spread

### In accordance with

EN 13501-1

### In accordance with

IMO FTP Code Part 1

### In accordance with

IMO FTP Code Part 2 and 5

## Thermal Properties

**Thermal Conductivity in 10 °C,  $\lambda_{10}$**  0.039 W/mK

**Thermal Conductivity in 50 °C,  $\lambda_{50}$**  0.044 W/mK

**Thermal Conductivity in 100 °C,  $\lambda_{100}$**  0.053 W/mK

Values announced by the manufacturer.



PAROC OY AB, P.O. Box 47 (Läkkisepäntie 23), FI-00621 Helsinki Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, www.paroc.com

The information in this data sheet represents the sole and comprehensive description of the condition of the product and its technical properties. However, the content of this data sheet does not mean granting a commercial guarantee. In so far as the product is used in an area of use which is not provided for in this data sheet, we cannot warrant its suitability for said area of use unless the suitability was expressly confirmed by us upon request. This data sheet replaces all previous ones. As a result of constant further development of our products we reserve the right to make alterations to data sheets. PAROC and red and white stripes are registered trade marks of Paroc Oy Ab. © Paroc Group 2009.