

Last Modified: 22.7.2010

PAROC Pro Lamella Mat AluCoat

(PAROC Lamella Mat 50 AluCoat)



Short Description

Stone wool lamella mat with a reinforced aluminium foil facing.

Application

Thermal and condensation insulation of air ducts and other ventilation ducts and equipment.

Application / Marine

Thermal insulation for ducts.

Technical Properties

Nominal Density

50 kg/m³

Maximum Operating Temperature

250 °C

The surface temperature of the facing must not exceed +80°C (temperature restriction determined in accordance with the heat resistance of adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Thickness

20-100 mm

Tolerances according to SFS 5454.

Packaging

Plastic

Package on Request

Pallet

Fire Properties

Reaction to Fire, Euroclass

A2 - s1, d0

Marine Fire Classification

Non-Combustible

Surface Flammability (Marine)

Low flame-spread

In accordance with

EN 13501-1

In accordance with

IMO FTP Code Part 1

In accordance with

IMO FTP Code Part 2 and 5

Thermal Properties

Thermal Conductivity in 10 °C, λ_{10} 0.039 W/mK

Thermal Conductivity in 100 °C, λ_{100} 0.053 W/mK

Thermal Conductivity in 200 °C, λ_{200} 0.085 W/mK

Values announced by the manufacturer.

Mechanical Properties


Compressive Stress at 10 % deformation (Declared), CS(10), In accordance with (σ_{10})

≥6 kPa

EN 826

Other Information

PAROC Pro Lamella Mat AluCoat can be used to satisfy the requirements as given in the tables for insulation thickness in BS5422:2009. Paroc can offer help and assistance to customers to confirm that the insulation systems proposed do in fact, achieve the necessary performance criteria. PAROC Pro Lamella Mat AluCoat conforms to BS3958-5.



PAROC OY AB, P.O. Box 47 (Läkkisepäntie 23), FI-00621 Helsinki Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, www.paroc.com

The information in this data sheet represents the sole and comprehensive description of the condition of the product and its technical properties. However, the content of this data sheet does not mean granting a commercial guarantee. In so far as the product is used in an area of use which is not provided for in this data sheet, we cannot warrant its suitability for said area of use unless the suitability was expressly confirmed by us upon request. This data sheet replaces all previous ones. As a result of constant further development of our products we reserve the right to make alterations to data sheets. PAROC and red and white stripes are registered trade marks of Paroc Oy Ab. © Paroc Group 2010