



PRO CLAD SYSTEM

RESISTANCE TO CHEMICAL SUBSTANCES



PAROC[®]

Clad-System (Surface of film)

Physical and chemical stability

Acids	Acetic acid (all concentrations)	resistant
	50% formic acid	resistant
	10% hydrochloric acid	resistant
	30% hydrochloric acid	partially resistant
	10% and 35% hydrofluoric acid	resistant
	10% nitric acid	resistant
	65% and 100% nitric acid	not resistant
	30% and 85% phosphoric acid	resistant
	20% sulphuric acid	partially resistant
	Sulphur dioxide gas, dry	resistant
80% and above sulphuric acid	not resistant	
Aldehydes	Acetaldehyde	resistant
	Formaldehyde	resistant
Alcohols	Benzyl alcohol	partially resistant
	Cyclohexanol	resistant
	Ethyl alcohol	resistant
	Glycerine	resistant
	Glycol	resistant
	Isopropyl alcohol	resistant
	Methyl alcohol	resistant
Aqueous alkaline solutions	Ammonium hydroxide	not resistant
	Calcium hydroxide	partially resistant
	Sodium hydroxide	not resistant
Chlorinated hydrocarbons	Carbon tetrachloride	partially resistant
	Chlorinated Biphenyls	partially resistant
	Chloroform	resistant
	Trichloroethylene	resistant
Esters	Ethyl acetate	resistant
Hydrocarbons	Aliphatic hydrocarbons	resistant
	Benzene	resistant
	Gasoline (petrol)	resistant
	Mineral oils	resistant
	Toluene	resistant
	Xylene	resistant
Other substances	Chlorine	resistant
	Hydrogen Peroxide	resistant
	Oxygen	resistant
	Water*	resistant
Other organic solutions	Acetone	resistant
	Diethyl ether	resistant
	Nitrobenzene	not resistant
	Phenol	not resistant
Salt solutions	Alkaline carbonates	resistant
	Bichromate	resistant
	Cyanide	resistant
	Fluorides	resistant

*Upon thermal stress by water above 100°C/water vapour Clad film tends to become brittle through hydrolysis.

Disclaimer of Warranty

The information contained in this brochure represent a conclusive description of product specifications or its technical properties and are valid as of the date of publication until the current brochure is superseded and replaced, digitally or in print, by a new version. However, any acceptance of guarantee may not be derived therefrom.

If products are used in an area of application not provided for in this brochure, we shall not assume any warranty for its suitability for the specific purpose, unless such suitability has been confirmed by us. We reserve the right of changes and adjustments due to constant further development of our products.

TIUK0420
© Paroc 2021

