

### **PRODUCT DATASHEET**

Contra Street	10000	A Carlos	a car	
South West	Real Property lies	150	31500	-
Station of the	The second	1.00	212	-
	the state	1 2	al a	
	the set	1 2	al a	
	1	4 2	a a	
	1	1. 2	Sec. A.	
			Sec. Se	
			a la	
			2 A	
			No. A.	
		-	N.A.	

## PAROC InVent 100 N1

Stone wool slab with grey glass fibre felt facing.

Thermal and acoustical insulation of air conditioning machines etc.

Surface temperature of the facing must not exceed 80°C (temperature restriction determined in accordance with heat resistance adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

**Certification Number Designation Code Nominal Density** 

0809-CPR-1016 Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo. Finland MW-EN 14303-T5-WS1

Package Type

100 kg/m<sup>3</sup> Plastic packs on pallet

DIMENSIONS			
WIDTH X LENGTH		THICKNESS	
600 x 1200 mm		15 - 100 mm	
According to EN 822		According to EN 823	
Other Dimensions: Other dimensions available on reques	t.		
PROPERTY	VALUE		ACCORDING TO

DIMENSIONAL STABILITY		
Maximum Service Temperature - Dimensional Stability	NPD	EN 14303:2009+A1:2013 (EN 14706)



#### Properties

PROPERTY	VALUE	ACCORDING TO
FIRE PROPERTIES		
Reaction to Fire, Euroclass	A1	EN 14303:2009+A1:2013 (EN 13501-1)
Continuous Glowing Combustion	NPD	EN 14303:2009+A1:2013
THERMAL PROPERTIES		
Thermal Conductivity in 10 °C, $\lambda_{10}$	0,037 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Dimensions and Tolerances	T5	EN 14303:2009+A1:2013
MOISTURE PROPERTIES		
Water Absorption, Short Term WS, (Wp)	≤ 1 kg/m²	EN 14303:2009+A1:2013 (EN 1609)
Water Vapour Diffusion Resistance	NPD	EN 14303:2009+A1:2013 (EN 12086)
Chloride lons, Cl-	NPD	EN 14303:2009+A1:2013 (EN 13468)
SOUND PROPERTIES		
Sound Absorption	NPD	EN 14303:2009+A1:2013 (EN ISO 354)
MECHANICAL PROPERTIES		
Compressive Stress at 10 % deformation CS(10), $\sigma_{10}$	NPD	EN 14303:2009+A1:2013 (EN 826)
EMISSIONS		
Release of Dangerous Substances	NPD	EN 14303:2009+A1:2013
DURABILITY OF FIRE AND THERMAL PROPERT	IES	
Durability of Reaction to Fire Against Ageing/Degradation	No change in reaction to fire properties for mineral wool products. The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of the product is related to the organic content, which cannot increase with time.	
Durability of Reaction to Fire Against High Temperature	The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.	
Durability of Thermal Resistance Against Ageing/Degradation	Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.	

#### Appearance

The start of MA-A-start of all	$O_{1} = - C_{1} = C_$
Facing Material	Gass fibre felt (grev)
	Glass lible left (gley)

# CE

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries international use (general information).