


PRODUCT DATASHEET



PAROC InVent 45 G5/N1

Stone wool slab with black glass fibre cloth facing on one side and grey glass fibre felt on other side.

Ventilation attenuation slab.

Surface temperature of the facing must not exceed $80^{\circ}C$ (temperature restriction determined in accordance with heat resistance adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C. 0809-CPR-1016 Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo.

Certification Number Designation Code Nominal Density Package Type

Finland MW-EN 14303-T5-WS1 45 kg/m³ Cartons on Pallet

DIMENSIONS				
WIDTH X LENGTH		THICKNESS		
600 x 1200 mm		50 - 100 mm		
According to EN 822		According to EN 823		
Other Dimensions: Other dimensions available on request.				
PROPERTY	VALUE		ACCORDING TO	

DIMENSIONAL STABILITY					
Maximum Service Temperature - Dimensional Stability	NPD	EN 14303:2009+A1:2013 (EN 14706)			



Properties

PROPERTY	VALUE	ACCORDING TO	
FIRE PROPERTIES			
Reaction to Fire, Euroclass	A1	EN 14303:2009+A1:2013 (EN 13501-1)	
Continuous Glowing Combustion	NPD	EN 14303:2009+A1:2013	
THERMAL PROPERTIES			
Thermal Conductivity in 10 °C, λ_{10}	0,037 W/mK	EN 14303:2009+A1:2013 (EN 12667)	
Dimensions and Tolerances	T5	EN 14303:2009+A1:2013	
MOISTURE PROPERTIES			
Water Absorption, Short Term WS, (Wp)	≤ 1 kg/m²	EN 14303:2009+A1:2013 (EN 1609)	
Water Vapour Diffusion Resistance	NPD	EN 14303:2009+A1:2013 (EN 12086)	
Chloride lons, Cl-	NPD	EN 14303:2009+A1:2013 (EN 13468)	
SOUND PROPERTIES			
Sound Absorption	NPD	EN 14303:2009+A1:2013 (EN ISO 354)	
MECHANICAL PROPERTIES			
Compressive Stress at 10 % deformation CS(10), σ_{10}	NPD	EN 14303:2009+A1:2013 (EN 826)	
EMISSIONS			
Release of Dangerous Substances	NPD	EN 14303:2009+A1:2013	
DURABILITY OF FIRE AND THERMAL PROPERT	IES		
Durability of Reaction to Fire Against Ageing/Degradation	No change in reaction to fire properties for mineral wool products. The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of the product is related to the organic content, which cannot increase with time.		
Durability of Reaction to Fire Against High Temperature	The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.		
Durability of Thermal Resistance Against Ageing/Degradation	Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.		

Appearance

Facing Material	Glass fibre cloth (black) and class fibre felt (crev)
Facing waterial	Glass libre dour (black) and glass libre left (grey)

CE

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries international use (general information).