


PRODUCT DATASHEET



PAROC Marine Slab 60

Stone wool slab. Also possible to use with facings AluCoat, G1, G2, G3, G4, G7, N3 and N5. See "Facings".

Thermal insulation on ships.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Type-Examination (Module B) certificate No. EUFI29-20002519-MED

Nominal Density

60 kg/m³

Package Type









Plastic packs on pallet

DIMENSIONS	
WIDTH X LENGTH	THICKNESS
600 x 1200 mm	50 - 120 mm
According to EN 822	According to EN 823
Other Dimensions: Other dimensions available on request.	

Properties

PROPERTY	VALUE	ACCORDING TO
FIRE PROPERTIES		
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1
THERMAL PROPERTIES		
Thermal Conductivity in 10 °C, λ_{10}	0,036 W/mK	EN 12667
Thermal Conductivity in 50 °C, λ_{50}	0,042 W/mK	EN 12667
Thermal Conductivity in 100 °C, λ_{100}	0,052 W/mK	EN 12667
Thermal Conductivity in 150 °C, λ_{150}	0,063 W/mK	EN 12667
Thermal Conductivity in 200 °C, λ_{200}	0,075 W/mK	EN 12667
Thermal Conductivity in 250 °C, λ_{250}	0,090 W/mK	EN 12667
MOISTURE PROPERTIES		
Water Absorption Short Term WS, (W_p)	$\leq 1 \text{ kg/m}^2$	EN 1609

Appearance

FACINGS				
				
	AluCoat	G1	G2	G3
				
	G4	G7	N3	N5



Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).