

## PRODUCT DATASHEET



### PAROC Marine Wired Mat 100

Stone wool wired mat with galvanized net. Also possible to use with facings AluCoat, G1, G2, G4 and G7. See "Facings".

Fire insulation on ships.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Type-Examination (Module B) certificate No. EUFI29-20002520-MED

**Nominal Density**

100 kg/m<sup>3</sup>

**Package Type**






Plastic Packs on Pallet

DIMENSIONS	
WIDTH X LENGTH	THICKNESS
Width 500/600/900/1000 mm, length 2000 - 8000 depending on thickness. mm	30 - 120 mm
According to EN 822	According to EN 823

## Properties

PROPERTY	VALUE	ACCORDING TO
<b>FIRE PROPERTIES</b>		
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1
<b>THERMAL PROPERTIES</b>		
Thermal Conductivity in 10 °C, $\lambda_{10}$	0,039 W/mK	EN 12667
Thermal Conductivity in 50 °C, $\lambda_{50}$	0,042 W/mK	EN 12667
Thermal Conductivity in 100 °C, $\lambda_{100}$	0,047 W/mK	EN 12667
Thermal Conductivity in 200 °C, $\lambda_{200}$	0,063 W/mK	EN 12667
Thermal Conductivity in 300 °C, $\lambda_{300}$	0,083 W/mK	EN 12667
Values announced by the manufacturer.		
<b>MOISTURE PROPERTIES</b>		
Water Absorption Short Term WS, ( $W_p$ )	$\leq 1 \text{ kg/m}^2$	EN 1609

## Appearance

FACINGS				
				
	AluCoat	G1	G2	G4
				
	G7			



Head Office: PAROC GROUP, P.O. Box240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, [www.paroc.com](http://www.paroc.com)

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).