

## PRODUCT DATASHEET



### PAROC Marine Slab 150

Stone wool slab. Also possible to use with facings AluCoat, G1, G2, G3, G4, G7, N3, N5 and N8. See "Facings".

Fire protection on ships.

Maximum service temperature for PAROC Marine Slab 150 is 660°C.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.


<b>Certification Number</b>	0809-CPR-1016 Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo, Finland
<b>Designation Code</b>	Type-Examination (Module B) certificate No. EUFI29-20002519-MED
<b>Nominal Density</b>	MV-EN 14303-T5-WS1
<b>Package Type</b>	150 kg/m <sup>3</sup> Plastic packs on pallet


DIMENSIONS	
WIDTH X LENGTH	THICKNESS
600 x 1200 mm	20 - 60 mm
According to EN 822	According to EN 823
Other Dimensions: Other dimensions available on request.	

## Properties

PROPERTY	VALUE	ACCORDING TO
<b>FIRE PROPERTIES</b>		
Fire Classification (IMO)	Non-Combustible	IMO FTP 2010 Code Part 1
<b>THERMAL PROPERTIES</b>		
Thermal Conductivity in 10 °C, $\lambda_{10}$	0,039 W/mK	
Thermal Conductivity in 50 °C, $\lambda_{50}$	0.042 W/mK	EN 12667
Thermal Conductivity in 100 °C, $\lambda_{100}$	0.046 W/mK	EN 12667
Thermal Conductivity in 200 °C, $\lambda_{200}$	0.060 W/mK	EN 12667
Thermal Conductivity in 300 °C, $\lambda_{300}$	0.081 W/mK	EN 12667
Thermal Conductivity in 400 °C, $\lambda_{400}$	0.110 W/mK	EN 12667
Thermal Conductivity in 500 °C, $\lambda_{500}$	0.147 W/mK	EN 12667
Thermal Conductivity in 600 °C, $\lambda_{600}$	0.192 W/mK	EN 12667
<b>MOISTURE PROPERTIES</b>		
Water Absorption Short Term $W_S$ , ( $W_p$ )	$\leq 1 \text{ kg/m}^2$	EN 1609
<b>DURABILITY OF FIRE AND THERMAL PROPERTIES</b>		
Durability of Reaction to Fire Against Ageing/Degradation	No change in reaction to fire properties for mineral wool products. The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of the product is related to the organic content, which cannot increase with time.	
Durability of Reaction to Fire Against High Temperature	The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.	
Durability of Thermal Resistance Against Ageing/Degradation	Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.	

## Appearance

FACINGS	
	 <div style="display: flex; justify-content: space-around; margin-top: 5px;"> <span>N3</span> <span>N5</span> <span>N8</span> </div>



Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, [www.paroc.com](http://www.paroc.com)

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).