


## PRODUCT DATASHEET



### PAROC Pro Slab WR 350 AluCoat

Non-combustible stone wool insulation slab with reinforced alulamine facing for thermal insulation of process tank walls, vessels, smaller rounded and other large cylindrical or flat surfaces. PAROC WR products are 3rd party tested and certified according to the most stringent class of the LABS conformity (paint wetting impairment) standard, VDMA-24364.

Thermal insulation slab for industrial applications.

Surface temperature of the facing must not exceed 80 °C (temperature restriction determined in accordance with heat resistance adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200 °C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000 °C.

**Certification Number**

0809-CPR-1016 Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo, Finland

**Designation Code**

MW-EN 14303-T3-ST(+)350-WS1-MV2-CL10

**Nominal Density**

40 kg/m<sup>3</sup>

**Package Type**

Plastic packs on pallet

| DIMENSIONS                                               |        |                                  |
|----------------------------------------------------------|--------|----------------------------------|
| WIDTH X LENGTH                                           |        | THICKNESS                        |
| 600 x 1200 mm                                            |        | 40 - 200 mm                      |
| According to EN 822                                      |        | According to EN 823              |
| Other Dimensions: Other dimensions available on request. |        |                                  |
| PROPERTY                                                 | VALUE  | ACCORDING TO                     |
| DIMENSIONAL STABILITY                                    |        |                                  |
| Maximum Service Temperature - Dimensional Stability      | 350 °C | EN 14303:2009+A1:2013 (EN 14706) |

## Properties

| PROPERTY                                                                                                                        | VALUE                                                                                                                                                                                                                                                    | ACCORDING TO                       |
|---------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------|
| <b>FIRE PROPERTIES</b>                                                                                                          |                                                                                                                                                                                                                                                          |                                    |
| Reaction to Fire, Euroclass                                                                                                     | A1                                                                                                                                                                                                                                                       | EN 14303:2009 (EN 13501-1)         |
| Continuous Glowing Combustion                                                                                                   | NPD                                                                                                                                                                                                                                                      | EN 14303:2009+A1:2013              |
| <b>THERMAL PROPERTIES</b>                                                                                                       |                                                                                                                                                                                                                                                          |                                    |
| Thermal Conductivity in 10 °C, $\lambda_{10}$                                                                                   | 0,036 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Thermal Conductivity in 50 °C, $\lambda_{50}$                                                                                   | 0,042 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Thermal Conductivity in 100 °C, $\lambda_{100}$                                                                                 | 0,053 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Thermal Conductivity in 150 °C, $\lambda_{150}$                                                                                 | 0,066 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Thermal Conductivity in 200 °C, $\lambda_{200}$                                                                                 | 0,083 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Thermal Conductivity in 250 °C, $\lambda_{250}$                                                                                 | 0,102 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Thermal Conductivity in 300 °C, $\lambda_{300}$                                                                                 | 0,125 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Thermal Conductivity in 350 °C, $\lambda_{350}$                                                                                 | 0,148 W/mK                                                                                                                                                                                                                                               | EN 14303:2009+A1:2013 (EN 12667)   |
| Dimensions and Tolerances                                                                                                       | T3                                                                                                                                                                                                                                                       | EN 14303:2009+A1:2013              |
| <b>MOISTURE PROPERTIES</b>                                                                                                      |                                                                                                                                                                                                                                                          |                                    |
| Water Absorption, Short Term WS, ( $W_p$ )                                                                                      | $\leq 1 \text{ kg/m}^2$                                                                                                                                                                                                                                  | EN 14303:2009+A1:2013 (EN 1609)    |
| Water Vapour Diffusion Resistance                                                                                               | MV2                                                                                                                                                                                                                                                      | EN 14303:2009+A1:2013 (EN 12086)   |
| Chloride Ions, Cl-                                                                                                              | < 10 ppm                                                                                                                                                                                                                                                 | EN 14303:2009+A1:2013 (EN 13468)   |
| PAROC WR slabs providing very low water absorption (< 0,1 kg/m <sup>2</sup> at temperatures up to 300 °C according to EN 1609). |                                                                                                                                                                                                                                                          |                                    |
| <b>SOUND PROPERTIES</b>                                                                                                         |                                                                                                                                                                                                                                                          |                                    |
| Sound Absorption                                                                                                                | NPD                                                                                                                                                                                                                                                      | EN 14303:2009+A1:2013 (EN ISO 354) |
| <b>MECHANICAL PROPERTIES</b>                                                                                                    |                                                                                                                                                                                                                                                          |                                    |
| Compressive Stress at 10 % deformation CS(10), $\sigma_{10}$                                                                    | NPD                                                                                                                                                                                                                                                      | EN 14303:2009+A1:2013 (EN 826)     |
| <b>EMISSIONS</b>                                                                                                                |                                                                                                                                                                                                                                                          |                                    |
| Release of Dangerous Substances                                                                                                 | NPD                                                                                                                                                                                                                                                      | EN 14303:2009+A1:2013              |
| <b>DURABILITY OF FIRE AND THERMAL PROPERTIES</b>                                                                                |                                                                                                                                                                                                                                                          |                                    |
| Durability of Reaction to Fire Against Ageing/Degradation                                                                       | No change in reaction to fire properties for mineral wool products. The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of the product is related to the organic content, which cannot increase with time. |                                    |
| Durability of Reaction to Fire Against High Temperature                                                                         | The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.                               |                                    |
| Durability of Thermal Resistance Against Ageing/Degradation                                                                     | Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.                                                            |                                    |

## Appearance

|                 |                               |
|-----------------|-------------------------------|
| Facing Material | Reinforced alulaminat facing. |
|-----------------|-------------------------------|



Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, [www.paroc.com](http://www.paroc.com)

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).