

PRODUCT DATASHEET



PAROC XES 200j

Frost insulation (Ecoprim)

Slab made of extruded polystyrene cellular plastic (XPS) with rebated edges

Cold and freezer-store insulation, floating floor and sandwich structures, floating landing stages. Concrete roofs, terraces, courtyard decks, parking, etc where normal loads are expected, insulation of outer cellar walls with high soil pressure. Edge shape: Folded.

Approval: CE-marked (EN 13164)

Package Type

Package on pallet

DIMENSIONS	
WIDTH X LENGTH	THICKNESS
585 x 1185 mm	50 mm
585 x 1185 mm	70 mm
585 x 1185 mm	100 mm

Properties

PROPERTY	VALUE	ACCORDING TO
FIRE PROPERTIES		
Reaction to Fire, Euroclass	NPD	EN 13164:2012+A1:2015 (EN 13501-1)
THERMAL PROPERTIES		
Thickness (mm)	Thermal Conductivity λ_D / Thermal Resistance R_D	
50	0,035 W/mK / 1,45 K/W	EN 13164:2012
70	0,035 W/mK / 2,00 K/W	EN 13164:2012
100	0,037 W/mK / 2,70 K/W	EN 13164:2012
Thickness Tolerance, T	T1	EN 13164:2012+A1:2015 (EN 823)
MOISTURE PROPERTIES		
Water Absorption, Long Term WL(T), Wlt	$\leq 0,7$ Vol %	EN 13164:2012+A1:2015 (EN 12087)
Water Absorption, Long Term by Diffusion WD(V)	≤ 1 Vol %	EN 13164:2012+A1:2015 (EN 12088)
MECHANICAL PROPERTIES		
Compressive Stress or Compressive Strength CS(10Y), σ_{10} , σ_m	200 kPa	EN 13164:2012+A1:2015 (EN 826)
EMISSIONS		
Release of Dangerous Substances	No emissions	EN 13164:2012+A1:2015
DURABILITY OF COMPRESSIVE STRENGTH AGAINST AGEING/DEGRADATION		
Compressive Creep $CC(i_1/i_2/y)\sigma_c X_{ct}$	CC(2/1,5/50)90	EN 13164:2012+A1:2015 (EN 1606)
DURABILITY OF FIRE AND THERMAL PROPERTIES		
Durability of Reaction to Fire Against Heat, Weathering, Ageing/Degradation	NPD	
Durability of Thermal Resistance Against Heat, Weathering, Ageing/Degradation	Do not change	
Freeze-thaw Resistance	FTCD2	EN 13164:2012+A1:2015 (12091)



Head Office: PAROC GROUP, P.O. Box 240 (Energiaukuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).