


PRODUCT DATASHEET



PAROC Pro Wired Mat 680 AL1

Stone wool wired mat with galvanized wire mesh, sewing wire and aluminum facing. Even available with stainless steel wire mesh and/or sewing wire.

Fire and thermal insulation of cylindrical, conic and level surfaces.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Certification Number	0809-CPR-1016 Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo, Finland
Designation Code	MW-EN 14303-T2-ST(+)680-WS1-CL10
Nominal Density	100 kg/m³
Package Type	Plastic Packs on Pallet

DIMENSIONS		
WIDTH X LENGTH		THICKNESS
Width 500/600/900/1000 mm, length 2000 - 8000 mm depending on thickness.		30 - 120 mm
According to EN 822		According to EN 823
PROPERTY	VALUE	ACCORDING TO
DIMENSIONAL STABILITY		
Maximum Service Temperature - Dimensional Stability	680 °C	EN 14303:2009+A1:2013 (EN 14706)

Properties

PROPERTY	VALUE	ACCORDING TO
FIRE PROPERTIES		
Reaction to Fire, Euroclass	A1	EN 14303:2009+A1:2013 (EN 13501-1)
Continuous Glowing Combustion	NPD	EN 14303:2009+A1:2013
THERMAL PROPERTIES		
Thermal Conductivity in 10 °C, λ_{10}	0,035 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 50 °C, λ_{50}	0,039 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 100 °C, λ_{100}	0,045 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 150 °C, λ_{150}	0,051 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 200 °C, λ_{200}	0,059 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 300 °C, λ_{300}	0,078 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 400 °C, λ_{400}	0,102 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 500 °C, λ_{500}	0,131 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 600 °C, λ_{600}	0,167 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 680 °C, λ_{680}	0,196 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Dimensions and Tolerances	T2	EN 14303:2009+A1:2013
MOISTURE PROPERTIES		
Water Absorption, Short Term WS, (W_p)	$\leq 1 \text{ kg/m}^2$	EN 14303:2009+A1:2013 (EN 1609)
Water Vapour Diffusion Resistance	NPD	EN 14303:2009+A1:2013 (EN 12086)
Chloride Ions, Cl-	< 10 ppm	EN 14303:2009+A1:2013 (EN 13468)
SOUND PROPERTIES		
Sound Absorption	NPD	EN 14303:2009+A1:2013 (EN ISO 354)
MECHANICAL PROPERTIES		
Compressive Stress at 10 % deformation CS(10), σ_{10}	NPD	EN 14303:2009+A1:2013 (EN 826)
EMISSIONS		
Release of Dangerous Substances	NPD	EN 14303:2009+A1:2013
DURABILITY OF FIRE AND THERMAL PROPERTIES		
Durability of Reaction to Fire Against Ageing/Degradation	No change in reaction to fire properties for mineral wool products. The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of the product is related to the organic content, which cannot increase with time.	
Durability of Reaction to Fire Against High Temperature	The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.	
Durability of Thermal Resistance Against Ageing/Degradation	Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.	

Appearance

Facing Material	Galvanized wire mesh and sewing wire. Aluminium facing.
-----------------	---



Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).