


PAROC Hvac Lamella Mat AluCoat



Certification Number	0809-CPR-1016 / Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo. Finland
Designation Code	MW-EN 14303-T4-ST(+)250-WS1-MV2-CL10
Short Description	Stone wool lamella mat with reinforced aluminium foil facing. For Marine applications also available with facing G4.
Application	Thermal and condensation insulation of air ducts and other ventilation ducts and equipment.

The notified body Eurofins Expert Services Ltd. (0809) performed and issued the certificates: Type-Examination (Module B) certificate No. VTT-C-11535-15-16

Surface temperature of the facing must not exceed 80°C (temperature restriction determined in accordance with heat resistance adhesive). PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Dimensions	
Width x Length	Thickness
Width 1000 or 500 mm. Length 2500 - 10000 mm depending on thickness.	20 - 100 mm
In accordance with EN 822	In accordance with EN 823

Dimensional Stability		
Property	Value	According to
Maximum Service Temperature - Dimensional Stability	250 °C	EN 14303:2009+A1:2013 (EN 14707)

Packaging

Package Type	Plastic Packs on Pallet
--------------	-------------------------

Fire Properties

Reaction to Fire		
Property	Value	According to
Reaction to Fire, Euroclass	A1	EN 14303:2009+A1:2013 (EN 13501-1)

Continuous Glowing Combustion		
Property	Value	According to
Continuous Glowing Combustion	NPD	EN 14303:2009+A1:2013

Other Fire Properties		
Property	Value	According to
Fire Classification (IMO)	Non-combustible	IMO FTP Code Part 1
Surface Flammability (IMO)	Low flame-spread characteristics	IMO FTP Code Part 2 and 5

Thermal Properties

Thermal Resistance		
Property	Value	According to
Thermal Conductivity in 10 °C, λ_{10}	0,038 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 50 °C, λ_{50}	0,047 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 100 °C, λ_{100}	0,059 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 150 °C, λ_{150}	0,074 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 200 °C, λ_{200}	0,091 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Thermal Conductivity in 250 °C, λ_{250}	0,110 W/mK	EN 14303:2009+A1:2013 (EN 12667)
Dimensions and Tolerances	T4	EN 14303:2009+A1:2013

Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term WS, W_p	$\leq 1 \text{ kg/m}^2$	EN 14303:2009+A1:2013 (EN 1609)

Water Vapour Permeability		
Property	Value	According to
Water Vapour Diffusion Resistance	MV2	EN 14303:2009+A1:2013 (EN 12086)

Rate of Release of Corrosive Substances

Trace Quantities of Water Soluble Ions and the pH Value		
Property	Value	According to
Chloride Ions, Cl ⁻	< 10 ppm	EN 14303:2009+A1:2013 (EN 13468)

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).