

PAROC Pro Slab 120



Certification Number	0809-CPR-1016 / Eurofins Expert Services Ltd, Kivimiehentie 4, FI-02150 Espoo, Finland
Designation Code	MW-EN 14303-T5-ST(+)-660-WS1-CL10
Short Description	Stone wool slab.
Application	Thermal insulation slab for industrial applications.
Nominal Density	120 kg/m ³

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200 °C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000 °C.

Dimensions

Dimensions	
Width x Length	Thickness
600 x 1000 mm	30 - 160 mm
In accordance with EN 822	In accordance with EN 823

Dimensional Stability		
Property	Value	According to
Maximum Service Temperature - Dimensional Stability	660 °C	EN 14303:2009+A1:2013 (EN 14706)

Other Dimensions Available on request.

Packaging

Package Type Plastic packs on pallet

Fire Properties

Reaction to Fire		
Property	Value	According to
Reaction to Fire, Euroclass	A1	EN 14303:2009+A1:2013 (EN 13501-1)

Continuous Glowing Combustion		
Property	Value	According to
Continuous Glowing Combustion	NPD	EN 14303:2009+A1:2013

Thermal Properties

Thermal Resistance		
Property	Value	According to
Thermal Conductivity in 50 °C, λ_{50}	0,042 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 100 °C, λ_{100}	0,046 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 150 °C, λ_{150}	0,052 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 200 °C, λ_{200}	0,060 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 250 °C, λ_{250}	0,069 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 300 °C, λ_{300}	0,081 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 400 °C, λ_{400}	0,110 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 500 °C, λ_{500}	0,147 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Thermal Conductivity in 600 °C, λ_{600}	0,192 W/mK	EN 14303:2009 +A1:2013 (EN 12667) .
Dimensions and Tolerances	T5	EN 14303:2009+A1:2013

Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term WS, W_p	$\leq 1 \text{ kg/m}^2$	EN 14303:2009+A1:2013 (EN 1609)

Rate of Release of Corrosive Substances

Trace Quantities of Water Soluble Ions and the pH Value		
Property	Value	According to
Chloride Ions, Cl ⁻	< 10 ppm	EN 14303:2009+A1:2013 (EN 13468)

Sound Properties

Acoustic Absorption Index		
Property	Value	According to
Sound Absorption	NPD	EN 14303:2009+A1:2013 (EN ISO 354)

Emissions

Release of Dangerous Substances to the Indoor Environment		
Property	Value	According to
Release of Dangerous Substances	NPD	EN 14303:2009+A1:2013

Durability

Durability of Reaction to Fire Against Ageing/Degradation

No change in reaction to fire properties for mineral wool products. The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of the product is related to the organic content, which cannot increase with time.

Durability of Reaction to Fire Against High Temperature

The fire performance of mineral wool does not deteriorate with high temperature. The Euroclass classification of the product is related to the organic content, which remains constant or decreases with high temperature.

Durability of Thermal Resistance Against Ageing/Degradation

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).