

PAROC Marine Mat 50 AluCoat

PAROC Marine Mat 50 AluCoat is a non-combustible stone wool mat with glass-fiber scrim reinforced aluminium foil facing for thermal insulation on ships.



Product datasheet 1.6.2026

Dimensions	Width x Length (mm)	Thickness (mm)
	500/600/900/1000 x 8000	30
500/600/900/1000 x 7000	40	
500/600/900/1000 x 6500	50	
500/600/900/1000 x 6000	60	
500/600/900/1000 x 5500	70	
500/600/900/1000 x 5000	80	
500/600/900/1000 x 4000	100	
500/600/900/1000 x 2500	120	

Nominal Density
50 kg/m³
Plastic packs on pallet

Product characteristics	Fire Classification (IMO 2010 FTP Code Annex 1)	Type-Examination (Module B) certificate(s)
	Part 1, Non-combustibility	74480/A2 MED, 74465/A2 UK
Part 5, Low Flame-Spread characteristics	74479/A2 MED, 74467/A2 UK	
Quality system	Surveillance (Module D) certificate(s)	
MED	SMS.MED2.D/93834/B.0	
UK	SMS.UK.D/93834/B.0	
Water absorption short term (EN 29767)	≤ 1 kg/m ²	
Thermal conductivity	See table below	

Mean temperature (°C)	10							
Thermal conductivity (W/mK)	0.034							

Fire Properties
PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Environmental Properties

PAROC stone wool products are made from clean, natural material. They are environmentally friendly throughout their lifecycle, causing no harm to nature during or after their use. Stone wool does not contain any ingredients or chemicals that prevent or impede recycling.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Paroc makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Paroc reserves the right to modify this document without prior notice. PAROC is a registered trademark of Paroc Group Oy. This data sheet is valid in following countries: International.