

PAROC AluCoat T

PAROC AluCoat T is a glass-fiber scrim reinforced aluminium facing with an adhesive layer. The longitudinal joints of the facing are sealed with a double-sided 25 mm wide tape, with total grammage of adhesive 70 g/m² (tolerance for the alternative with hotmelt adhesive: +/- 20 g/m² and tolerance for the alternative with synthetic rubber adhesive: +/- 9 g/m²) and carrier grammage of 17 g/m² (tolerance for the alternative with hotmelt adhesive: +/- 10 g/m² and tolerance for the alternative with synthetic rubber adhesive: +/- 2 g/m²).

PAROC AluCoat T is used on PAROC stonewool pipe sections.



Product datasheet

1.7.2025

Properties	Total grammage (without tape)	60 - 88.4 g/m ² , tolerance (-5...+6 g/m ²)
	Aluminium layer thickness	0.012-0.018 mm

Product characteristics	Fire Classification (IMO 2010 FTP Code Annex 1)	Type-Examination (Module B) certificate(s)
	Part 5, Low Flame-Spread characteristics	74479/A2 MED, 74467/A2 UK
	Quality system	Surveillance (Module D) certificate(s)
	MED	SMS.MED2.D/94701/A.2, SMS.MED2.D/93834/A.4
	UK	SMS.UK.D/94701/A.2, SMS.UK.D/93834/A.3

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Paroc makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Paroc reserves the right to modify this document without prior notice. PAROC is a registered trademark of Paroc Group Oy. This data sheet is valid in following countries: International.