

PRODUCT DATASHEET

PAROC BlackCoat Tape



PAROC BlackCoat Tape is a reinforced aluminum foil tape with a black color lacquer finish acrylic pressure sensitive adhesive and siliconized release paper liner.

It is ideal for sealing the joints when using PAROC BlackCoat products such as sections, lamella mats or slabs. PAROC BlackCoat Tape gives a great finish and safe installation.

Package Type	50mm: 24 rolls / box, 24 boxes/pallet
	75mm: 16 rolls / box, 24 boxes/pallet
	110mm: 12 rolls / box, 24 boxes/pallet

DIMENSIONS	
Thickness	0,068 mm
Width	50, 75, 110 mm
Length	50 m

Properties

PROPERTY	VALUE	ACCORDING TO
OTHER PROPERTIES		
Backing: Release liner: Adhesive: Adhesive strength: Apply at: Temperature range:	Glass-scrim reinforced aluminum with black finish Siliconized paper Acrylic min 20 N / 25 mm after 24 h +10 °C to + 40 °C -40 °C to +200 °C	AFERA 5001

Appearance

Facing Material	Glass-scrim reinforced aluminum with black finish, aluminum thickness 0,018 mm
COLOURS	
Black	

Handling

INSTALLATION	
Work Descriptions	During the installation, the insulation material to be taped should be at a minimum temperature of +10 °C. Allow the temperature of the insulating material to adjust to the ambient installation temperature. Make sure that the surfaces to be joined with tape are clean, dry free of dust, grease and solvents before film/tape application. Do not use cleaners containing anti-adhesive agents. Some plastics and paints may discharge anti-adhesive agents leading to bonding failure. Rough and uneven surfaces may weaken bonding.
Handling and Storage	Product should be stored in original packaging, laid flat on the slit edge of the roll. Storage in dry and clean areas, at normal temperature, protected from direct sunlight and heat sources. Storage conditions: +10 °C to +30°C, under dry conditions inside a warehouse, protected from UV.

We strongly advise users to test the product ‘s suitability for their own particular requirement. All data and recommendations contained in this Technical Data Sheet are based on our own test results and practical experience and are aimed at helping customers select the appropriate tape for a given application.

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Paroc makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Paroc reserves the right to modify this document without prior notice. PAROC is a registered trademark of Paroc Group Oy. This data sheet is valid in following countries: International..